Technical Details

Burch



Repeats Not Shown to Scale

Mezzanine Marina 1012448

Meets or exceeds all ACT® Standards

Made in the USA **Bleach Cleanable** PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

| Content | 100% Polyester |
|------------------|---|
| Finish | Crypton |
| Backing | Crypton |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 18.8 oz. per linear yd |
| Width | 54" |
| Roll Size | 50 yards |
| Ends/Picks | Ends: 145 per inch Picks: 32 per inch |
| Repeat | H - 4.5 " V - 5.4 " |
| Directional | Yes |
| Railroaded | No |
| Made in the USA | Yes |
| | |

Additional Attributes

PFAS Free

Certifications

Greenguard Gold Certified

Yes - Crypton Technology is Greenguard Gold Certified

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Yes

Crypton Seating Fabric



Performance Characteristics

| Abrasion Resistance ASTM D4157 | 95,000 double rubs* | |
|-----------------------------------|--------------------------------------|--|
| Brush Pill ASTM D3511 | 4 | |
| Tensile Strength ASTM D5034 | Warp: 272.5 lbs. Fill: 169.6 lbs. | |
| Tear Strength ASTM D2262 | Warp: 47.5 lbs. Fill: 30.1 lbs. | |
| Seam Slippage ASTM D4034 | Warp: 96.8 lbs. Fill: 64.4 lbs. | |
| Colorfastness to Crocking AATCC 8 | Dry: 4.5 Wet: 4.5 | |
| Colorfastness to Light AATCC 16 | Hours: 40.0 Class: 4.0 | |
| Flammability** | | |
| CAL TB 117-2013 | Passes | |
| NFPA 260 | Class 1 | |
| UFAC | Class 1 | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Toll Free 1.800.841.8111